

## PRODUCT SUMMARY

Valspar® Trade Direct to Wood and Metal is a high-quality, water-based and quick drying exterior paint that is showerproof in 30 minutes. Specifically formulated for bare or rusty metal, cast iron, galvanized steel, aluminium and stainless steel, wood and timber, this emulsion can be applied direct to rust - no primer needed. With our 10 year-all weather protection, Direct to Wood & Metal promises superior longevity. Valspar® Trade - formulated for the perfect finish.

## PRODUCT FEATURES & BENEFITS

- Direct to rust – no primer needed
- Showerproof in 30 minutes
- 10 Year All-Weather Protection

## RECOMMENDED USES/SUBSTRATES

- Bare metal
- Rusted steel
- Cast iron
- Galvanised steel
- Aluminium
- Stainless steel
- Wood

## SPRAYER GUIDE

Application method: Brush, roller or sprayer

Finish	Eggshell	Satin
Sprayer	FC 4000 18V	FC 4000 18V
Front End	Finespray	Finespray
Air Volume	10-11	10
Material Volume	5	6
Dilution	5-10%	5-10%

\*Derived from usage patterns of Wagner sprayers

## SHIPPING & PACKAGING

Freight classification: Paint or paint related material. Protect from freezing.

Packaging: Case of 1

**SHERWIN-WILLIAMS.**

## SURFACE PREPARATION

Read health and safety information before painting. Do not apply in damp or humid conditions. Ensure the surface temperature is above 10°C. Remove grease, algae and dust completely for a clean & dry surface. For previously painted surfaces, wash, sand, and remove loose or flaky paint. Sand all surfaces before painting. Repair any damaged areas. Wait 4-6 weeks before painting new surfaces. Valspar Trade Wood and Metal is a Direct to source product, if an additional primer is suitable in the location working, please apply one coat or spot prime with Valspar Trade Metal Primer.

## APPLICATION

Stir paint thoroughly. Mix containers of the same colour for uniformity. Apply 2 coats using a suitable brush, roller, or sprayer. Avoid excessive rolling or brushing. Apply liberally, working from dry areas into wet edges. Extra coats may be needed for dramatic colour changes. We recommend 3 coats for rusty metal. Dries to touch in approximately 1 hour. Wait 2-4 hours before applying the next coat. Do not thin this product if applying with a brush or roller. When you dilute the paint, you dilute the quality.

## STORAGE & DISPOSAL

**CLEAN UP:** Remove as much product from application equipment before cleaning. Do not wash paint down the drain when washing brushes and rollers. Clean painting tools with warm, soapy water. Wipe up spills immediately with a damp cloth.

**STORAGE & DISPOSAL:** Please dispose of unused paint responsibly. Check with your local authority to see if they provide facilities for the disposal of waste paint. If you have leftover paint that cannot be re-used or stored, do not empty into drains or watercourses. Protect from frost.

## HEALTH & SAFETY

Read carefully and follow all instructions. Keep out of reach of children. If medical advice is needed, have product container or label at hand. Contains a biocidal product: 1,2-benzisothiazol-3(2H)-one, reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1), 2-methylisothiazol-3(2H)-one and 3-aminopropyltriethoxysilane. May produce an allergic reaction. Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist. EU limit for this product (Cat A/i): 140g/l (2010). This product contains a maximum VOC content of 50 g/l. Water-based paint. Ensure good ventilation during drying and application. When applying it is advisable to wear eye protection. Avoid inhalation of dust, wear a face mask when dry sanding. Special precautions should be taken during the surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead.

## PRODUCT SPECIFICATION

**Product Type:**

Acrylic water-based paint

**Viscosity:**

80-105 KU

**Sheen:**

Eggshell: 10-20 at 60°  
Satin: 20-30 at 60°  
Gloss: 75-100 at 60°

**VOC:**

Trace

**Solid content of base (before colourant):**

Base A: 30-40%  
Base B: 30-37%  
Base C: 30-32%  
PBW: 30-40%

**Coverage:**

12m<sup>2</sup>/L

**Touch dry:**

1 hour

**Recoat:**

2 - 4 hours

**Application temperature:**

Apply in dry conditions above a minimum temperature of 10°C.

**Storage temperature:**

5 - 38°C – do not freeze

**Certifications:**



If you require further support, please contact Valspar Customer Service on **0344 736 9174 (UK) / 35319075488 (ROI)** or [customerservice@valsparpaint.co.uk](mailto:customerservice@valsparpaint.co.uk)

Sherwin-Williams UK Limited, Avenue One, Station Lane, Witney, Oxfordshire, OX28 4XR, UK  
Sherwin-Williams (Ireland) Ltd, Registered in Ireland 088980, Unit 53, Robinhood Industrial Estate, Dublin 22, D22 PW99